



Ensayo de doblado / desdoblado		
Diámetro de los mandriles (mm)		
Φ (mm)	B 400 S	B 500 S
6	30	36
8	40	48
10	50	60
12	60	72
14	70	112
16	80	128,00
20	160	200
25	200	250
32	320	384
40	400	480